



nyloflex® FSC Digital

Soft plate for corrugated postprint, especially for transit packaging
– unique hardness in the solid plates segment

Low plate hardness & high print quality

- perfect area coverage, particularly on low cost liners
- very good ink transfer
- good intermediate depths
- excellent print results, particularly in solid areas
- superior printing performance in line work
- suitable for screen work

Standard solid plate processing – cost efficient & reliable

- superior durability and long lasting lifetime
- suitable for standard equipment – no additional investment necessary
- established technology – no additional training required
- easy handling – clean and fast processing
- reduced plate cleaning cycles

Advantages of nyloflex® Digital

- superior printing quality with sharper images, more open intermediate depths
- increased productivity and data transfer without loss of quality due to digital workflow
- consistency in quality when repeating plate processing
- cost effective and more environmentally friendly in processing, as no film is required

nyloflex® FSC Digital

	nyloflex® FSC Digital			
	318	394	470	550
Technical characteristics				
Base material	polyester film			
Colour of raw plate	orange, with black LAMS layer			
Total thickness¹ (mm)	3.18	3.94	4.70	5.50
(inch)	0.125	0.155	0.185	0.217
Hardness acc. to DIN 53505 (Shore A)	26	26	26	26
Plate hardness (Shore A)	30	28	27	26
Relief depth (mm)	0.9 – 1.5	1.0 – 1.5	1.2 – 2.2	2.0 – 3.0
Tonal range (%)	3 – 95	3 – 95	3 – 95	3 – 95
at screen ruling	32 l/cm (80 lpi)	32 l/cm (80 lpi)	24 l/cm (60 lpi)	24 l/cm (60 lpi)
Fine line width (down to µm)	300	300	300	300
Isolated dot diameter (down to µm)	750	750	750	750

Processing parameters²				
Back exposure (s)	50 – 100	50 – 100	70 – 100	120 – 160
Main exposure (min)	10 – 14	10 – 14	10 – 14	10 – 14
Washout speed (mm/min)	130 – 140	90 – 100	60 – 70	50 – 60
Drying time at 60 °C / 140 °F (h)	2.5 – 3.0	3.0	3.5	4.0
Post exposure UV-A (min)	10	10	10	10
Light finishing UV-C (min)	10 – 15	10 – 15	10 – 15	10 – 15

¹ Standard thicknesses currently available – subject to change.

² All processing parameters depend on, among others, the processing equipment, lamp age and the type of washout solvent. The above mentioned processing times were established under optimum conditions on nyloflex® processing equipment and using nylosolv® washout solvents. The values for the main exposure of digital plates were determined at an exposure intensity of > 15mW/cm². Under other conditions the processing times can differ from these. Therefore the above mentioned values are only to be used as a guide.

Suitable equipment

The nyloflex® FSC Digital can be processed with nyloflex® processing equipment and all similar devices. The nyloflex® FSC Digital can be used with all laser systems suitable for imaging flexo printing plates.

Printing inks

Suitable for all water based printing inks.

Washout solvents

Especially good results are achieved with nylosolv® washout solvents. nylosolv® can be distilled and reused.

Processing information

A detailed description of the individual platemaking steps, as well as detailed information about processing and storing can be found in the nyloflex® User Guide.

High quality standard

nyloflex® printing plates are manufactured according to DIN ISO 9001 and DIN ISO 14001 standards and requirements. This process in accordance with environmental management requirements, guarantees our customers consistent high quality products and services.

You are welcome to contact us for further information.

Flint Group Flexographic Products
Sieglestrasse 25
70469 Stuttgart
Germany

T +49 711 9816-301
F +49 711 9816-801
info.flexo@flintgrp.com
www.flintgrp.com

All information in this document is based on our present knowledge and experience at the time of printing. Due to the multitude of factors influencing the processing and application of our products, it does not exempt the user from testing and calibrating. Nor does it imply any legally binding assurance concerning specific properties of the products or the suitability for a particular application. The responsibility of observing any possible industrial property rights, laws and regulations is the obligation of the user. Subject to technical changes without prior notice. Names marked ® are registered trademarks of Flint Group.